

DESCRIPTION

Equipment and method for manufacturing a soot preform

Technical Field

5 The present invention relates to equipment and a manufacturing method for manufacturing a soot preform for an optical fiber, photomask or the like.

Background Art

10 For manufacturing a soot preform there are widely used methods, such as the VAD method and the OVD method. According to these methods, the gas of raw materials such as silicon tetrachloride and germanium tetrachloride is supplied to a burner together with a combustion gas and the like, and glass particulates that are formed by hydrolysis reaction therefrom are deposited on
15 the tip of or around a starting rod. The soot preform thus produced is dehydrated and sintered, resulting in a transparent vitrified preform. The transparent glass preform is melted by heating, and drawn to form an optical fiber.

 Figure 4 is a sectional view illustrating the main part of equipment in
20 which a soot preform is produced. The numeral 1 shows a reaction vessel, 2 a burner, 2a flame, 3 an air inlet, 4 an exhaust port, 5 a starting rod, 6 a soot preform, and 7 the flow of an air current.

Gases, such as a raw material gas comprising silicon tetrachloride,

09807372.071601

consequently were unlikely to cause any special problem. Also, when the number of the voids having a diameter equal to or more than 1 mm that existed in the preforms was examined about 10 pieces of the above preforms that were in a state transparently vitrified by dehydration and sintering, the existence of
5 0.9 voids per preform was confirmed.

(Comparative example)

After manufacturing 10 pieces of preforms 6 in the same manner as in Example 1 except that the partition board 8 was not provided, the inside of the reaction vessel was examined. The quantity of the floating glass particulates
10 that adhered to the inner wall surface in the space above the partition board 8 of the reaction vessel was considerably large. Also, when the number of the voids having a diameter equal to or more than 1 mm that existed in the preforms was examined about 10 pieces of the above preforms that were in a state transparently vitrified by dehydration and sintering, the existence of
15 voids per preform was confirmed. The number of voids is considerably larger as compared with Examples 1, 2, and 3. It is considered to be due to the numerous floating glass particulates that adhered to the soot preform.

The applicability in the industry

20 The soot preform manufacturing equipment of the present invention is constituted such that a partition board is provided in part of the space around a soot preform in a reaction vessel so that the space is separated into the upper and lower parts. An exhaust port is provided below the partition board in the

09807372-071601

1363037 E 07 J

5
10
15